

Swisspearl Largo

Version: 6/26

Façade Boards

EN 12467

Avera | Vintago | Reflex

Avera is a naturally dried, through-coloured fibre-cement panel manufactured using a dynamic production process that gives it an unmistakably natural and authentic texture. The highly resistant transparent coating makes the panels particularly scratch resistant and protects them from heavy soiling and graffiti.

Vintago is a naturally dried fibre-cement panel that features a sanded and slightly rough surface. Through a polishing process using a coarse abrasive grit, the interior and the original character of the fibre-cement board are subtly brought to the surface.

Reflex adds a reflective coating that creates a distinctive light reflection.



VINTAGO

transparent High-Resistant Coating
 sanded
 coloured through

VI 061
 VI 021
 VI 040
 VI 050
 VI 100
 VI 011
 VI 091
 VI 001
 VI 071
 VI 031



AVERA

transparent High-Resistant Coating
 coloured through

AV 060
 AV 020
 AV 040
 AV 050
 AV 100
 AV 010
 AV 000
 AV 070
 AV 030



REFLEX

iridescent, opaque High-Resistant Coating
 coloured through

Granite 4161
 Granite 4162
 Anthracite 4021
 Anthracite 4022
 Jade 4051
 Crystal 4112
 Crystal 4111
 Ivory 4091
 Ivory 4092
 Amber 4071
 Amber 4072
 Coral 4031



Swisspearl Largo



	Units	6 mm	8 mm	12 mm
Dimension (nominal)				
Thickness	mm	6.0	8.0	12.0
Width	mm	1192 1250	1192 1250	1192 1250
Length	mm	2510 3050	2510 3050	2510 3050
Dimension tolerance (EN 12467, Level 1)				
Thickness (up to 20 mm)	mm	± 0.6	± 0.8	± 1.2
Width (1000 mm < a < 1600 mm)	mm	± 0.3 % a	± 0.3 % a	± 0.3 % a
Length (1600 mm < a)	mm	± 5.0	± 5.0	± 5.0
a is the nominal width or length				
Physical properties				
Density, dry minimum (EN 12467)	Kg/m ³	≥ 1550	≥ 1550	≥ 1550
Density, dry average (EN 12467)	Kg/m ³	1800	1800	1800
Weight (average shipping weight)	Kg/m ²	12.4	16.6	24.8
Mechanical properties				
Bending modulus of elasticity MOE (EN 12467)				
E-module average, ambient	GPa	12.0	12.0	12.0
Bending strength MOR (EN 12467)				
Wet average (EN 12467)	MPa	25.3	25.3	25.3
Minimum Class A4 (EN 12467)	MPa	18.0	18.0	18.0
Color variation measured on the production line				
CIELAB colour model	ΔE	< 2.0	< 2.0	< 2.0
Color Resistance to UV (Xenon Arc light for accelerated weathering) ASTM G155				
3000 hours	ΔE	< 5.0	< 5.0	< 5.0
5000 hours	ΔE	< 5.0	< 5.0	< 5.0
Environmental footprint (EN 15804 ISO 14040/ ISO 14044)				
GWP-total (A1-C4)	kgCO ₂ -eq		16,7	
GWP-biogenic (A1-C4)	kgCO ₂ -eq		0,74	
GWP-fossil (A1-C4)	kgCO ₂ -eq		16,5	

Swisspearl Largo

SWISSPEARL


	Units	6 mm	8 mm	12 mm
Thermal properties				
Coefficient of thermal expansion λ_{10}	mm/m °C	0.01	0.01	0.01
Temperature (air) in use	°C max	-40 +80	-40 +80	-40 +80
Frost resistance (100 cycles EN 12467)	RL	RL > 0,75	RL > 0,75	RL > 0,75
Thermal conductivity (ISO 8301, EN 12667) λ_{10}	W/mK	0.5	0.5	0.5
Hygrothermal properties				
Moisture movement (30/90 % RH, EN 12467)	mm/m	1.5	1.5	1.5
Moisture movement (wet-dry-wet)	mm/m	< 5	< 5	< 5
Moisture content	%	2 - 7	2 - 7	2 - 7
Water vapour transmission properties (ISO 12572)				
Vapour performance	kg/m² s Pa	0,03	0,03	0,03
Vapour transmission resistance (Z-value)	GPa m² s/kg	30,7	30,7	30,7
Vapour transmission resistance	s/m	224892	224892	224892
Vapour resistivity	Sd (m)	3,77	5	7,55
Vapour resistance factor, μ	MN s/(gm)	3840	3840	3840
Fire Performance				
Reaction to fire (EN 13501-1)		A2-s1. d0	A2-s1. d0	A2-s1. d0
Other properties				
Category, class (EN 12467)		NT A4	NT A4	NT A4

Impact resistance test (EAD 090062-01-0404) 8 mm + 12 mm

		Max.	Category IV	Category III	Category II	Category I
Hard body	1 Joule	Passed				
	3 Joule					
	10 Joule					
Soft body	10 Joule	Passed				Passed with ghost battens
	60 Joule					
	300 Joule					
	400 Joule	Not Passed				

*Installation principles determine the classification, contact product compliance for further information

Visual Appearance



Certifications

In compliance with European Regulation (EU) No. 305/2011 (Construction Products Regulation – CPR), the manufacturer provides a Declaration of Performance (DoP) for the product, confirming that it bears the CE marking. This marking indicates that the product meets the essential requirements set out in the applicable harmonized European standard. The Declaration of Performance, issued under the CPR, is available at www.swisspearl.com



The manufacturing facility holds the latest versions of the following ISO certificates.

- ISO 9001 Quality Management System

Disclaimer

This Product Data Sheet reflects typical values based on current production. While we aim to maintain consistent quality, minor variations may occur. Please note that all values are subject to an AQL level and tolerance in accordance with EN 12467. Key performance indicators (KPIs) are monitored and reviewed annually to ensure product reliability and continuous improvement.

The information provided serves as a general guide and may be updated without notice. We recommend validating the product for your specific application before use.

The material is made from natural raw materials; therefore, each individual fibre-cement product has its own unique appearance and texture. Inclusions, impurities, and irregularities may occur, such as uneven surfaces or textures, which are part of the product's natural look and feel. Natural imperfections may be visible; however, the overall appearance of the product will be homogeneous. These characteristics do not affect the strength or durability of fibre-cement products. Over time, the appearance of fibre-cement products will change as a result of exposure to environmental factors.

The values given are typical values

*: If any recipe or production process changes, the verification period is accordingly revised.

NA: Not applicable

NR: Not relevant