

Reaction to fire classification report No. 22082AV

Owner of the classification report

TRESPA INTERNATIONAL BV
Wetering 20
6002 SM Weert
The Netherlands

Introduction

This classification report defines the classification assigned to the product ***'Trespa® Toplab® Vertical'*** in accordance with the procedures given in the standard EN 13501-1:2018: Fire classification of construction products and building elements - Part 1: classification using data from reaction to fire tests.

This classification report consists of 14 pages and may only be used or reproduced in its entirety

1. DETAILS OF CLASSIFIED PRODUCT

a) General

The product **Trespa® Toplab® Vertical** is defined as a 'High Pressure Laminate (HPL) panel'.

Its classification is valid for the following end use application(s):

Used as HPL panels for internal wall and ceiling finishes.

b) Product description

This description is based on information given by the sponsor.

Core type 1	Nominal values (1)
Trespa® Toplab® Vertical	
Material	Single sided or double-sided STD grade high pressure laminate (HPL), suitable for interior applications. The material consists of kraft paper impregnated with phenolic resin and a coat on the outside with acrylic resin.
Manufacturer	Trespa International B.V.
Core type	Core type 1 (3)
Total thickness (mm)	6 - also valid for all higher thicknesses
Total density (kg/m ³)	1350
Use of fire retardants	No
Colour of the coating on the decor side	
<i>Printed colourgroup (NA,NM,NW,C,CM)</i>	Valid for all colours
<i>UNI colourgroup (A,L)</i>	Valid for all colours
<i>Metallics colourgroup (M,LM)</i>	Valid for all colours
Surface texture	Satin, matt-rock, diffuse, oblique, specular and matt (see Figure 1)
Organic content of the coating on the decor side (g/m ²)	(2)
Colour group	UNI (A,L) ,Printed (NA,NM,NW,C,CM) and Metallics (M,LM)

(1) Based on the information given by the sponsor

(2) Confidential information of the sponsor, not known by the laboratory

(3) Known by the laboratory

Core type 2		Nominal values (1)
Trespa® Toplab® Vertical		
Material	Single sided or double-sided STD grade high pressure laminate (HPL), suitable for exterior and interior applications. The material consists of natural fibers impregnated with phenolic resin and a coat on the outside with acrylic resin.	
Manufacturer	Trespa International B.V.	
Core type	Core type 2 (3)	
Total thickness (mm)	8 - also valid for all higher thicknesses	
Total density (kg/m ³)	1350	
Use of fire retardants	No	
Colour of the coating on the decor side		
	<i>Printed colourgroup (NA,NM,NW,C,CM)</i>	Valid for all colours
	<i>UNI colourgroup (A,L)</i>	Valid for all colours
	<i>Metallics colourgroup (M,LM)</i>	Valid for all colours
Surface texture	Satin, matt-rock, diffuse, oblique, specular and matt (see Figure 1)	
Organic content of the coating on the decor side (g/m ²)	(2)	
Colour group	UNI (A,L) ,Printed (NA,NM,NW,C,CM) and Metallics (M,LM)	

(1) Based on the information given by the sponsor

(2) Confidential information of the sponsor, not known by the laboratory

Core type 3	Nominal values (1)
Trespa® Toplab® Vertical	
Material	Double-sided STD grade high pressure laminate (HPL), suitable for exterior and interior applications. The material consists of a mixture of impregnated kraft and impregnated natural fibers and a coat on the outside with acrylic resin.
Manufacturer	Trespa International B.V.
Core type	Core type 3 (3)
Total thickness (mm)	6 - also valid for all higher thicknesses
Total density (kg/m ³)	1350
Use of fire retardants	No
Colour of the coating on the decor side	
<i>UNI colourgroup (A,L)</i>	Valid for all colours
<i>Metallics colourgroup (M,LM)</i>	Valid for all colours
Surface texture	Satin, matt-rock, diffuse, oblique, specular and matt (see Figure 1)
Organic content of the coating on the decor side (g/m ²)	(2)
Colour group	UNI (A,L) ,Printed (NA,NM,NW,C,CM) and Metallics (M,LM)

(1) Based on the information given by the sponsor

(2) Confidential information of the sponsor, not known by the laboratory



Figure 1: different types of surface textures for the STD grade high pressure laminate (HPL)

More details (e.g. mounting and fixing) are available in the test report(s) in support of this classification (§2a).

2. TEST REPORTS AND EXAP REPORTS AND TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION

a) Test reports (and EXAP reports)

Name of the laboratory	Name of the sponsor	Test report ref. No. and test date	Test method and date
WFRGENT nv Ghent, Belgium	TRESPA INTERNATIONAL BV	22082X:08/11/2022 22082Y:28/10/2022 22082Z: 08/11/2022 22082AA: 08/11/2022 22082AB: 28/10/2022 22082AC: 08/11/2022 22082AD: 08/11/2022 22082AE: 28/10/2022 22082AF: 08/11/2022 22082AG: 28/10/2022 22082AH: 08/11/2022	EN ISO 11925-2:2020
WFRGENT nv Ghent, Belgium	TRESPA INTERNATIONAL BV	22082L:18/11/2022 & 19/11/2022 22082M:26/10/2022 22082N:26/11/2022 22082P:22/11/2022 & 23/11/2022 22082Q:31/10/2022 22082R:14/11/2022, 16/11/2022 & 17/11/2022 22082S:10/11/2022 & 12/11/2022 22082T:26/10/2022 & 27/10/2022 22082U: 14/11/2022 22082V:29/10/2023 & 31/10/2023 22082W:14/11/2022 , 24/11/2022 & 26/11/2022	EN 13823:2020+A1:2022
WFRGENT nv Ghent, Belgium	TRESPA INTERNATIONAL BV	22082AR	EXAP according to CEN/TS 15117 (August 2005)

b) Test results

Official test results used for the classification ()**

Test method	Parameter	Number of tests	Results		Criteria for Class D-s2,d0	
			Continuous parameters Mean	Compliance parameters	Continuous parameters	Compliance parameters
EN ISO 11925-2 (*) (1) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	$F_s \leq 150$ mm Ignition filter paper $F_s \leq 150$ mm Ignition filter paper	6 6	(-) (-) (-) (-)	Yes No Yes No	(-) (-) (-) (-)	Yes No Yes No
(*) The material didn't melt nor pull away from the pilot burner. (1) Based on the results obtained in test report No. 22082X – CORE TYPE 1 – NA17 – MATT ROCK – 8 mm						
EN ISO 11925-2 (*) (2) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	$F_s \leq 150$ mm Ignition filter paper $F_s \leq 150$ mm Ignition filter paper	6 6	(-) (-) (-) (-)	Yes No Yes No	(-) (-) (-) (-)	Yes No Yes No
(*) The material didn't melt nor pull away from the pilot burner. (2) Based on the results obtained in test report No. 22082Y - CORE TYPE 1 – A.12.1.8 – SATIN – 8 mm						
EN ISO 11925-2 (*) (3) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	$F_s \leq 150$ mm Ignition filter paper $F_s \leq 150$ mm Ignition filter paper	6 6	(-) (-) (-) (-)	Yes No Yes No	(-) (-) (-) (-)	Yes No Yes No
(*) The material didn't melt nor pull away from the pilot burner. (3) Based on the results obtained in test report No. 22082Z - CORE TYPE 1 – M21.8.1 – OBLIQUE – 8 mm						
EN ISO 11925-2 (*) (4) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	$F_s \leq 150$ mm Ignition filter paper $F_s \leq 150$ mm Ignition filter paper	6 6	(-) (-) (-) (-)	Yes No Yes No	(-) (-) (-) (-)	Yes No Yes No
(*) The material didn't melt nor pull away from the pilot burner. (4) Based on the results obtained in test report No. 22082AA - CORE TYPE 1 – NA17 – MATT ROCK – 6 mm						

(-) Not applicable

(**) The internal product definitions are, in comparison with the test reports and the exap report, mentioned without the resin type and core type. The resin type and core type are known by the laboratory.

Official test results used for the classification ()**

Test method	Parameter	Number of tests	Results		Criteria for Class D-s2,d0	
			Continuous parameters Mean	Compliance parameters	Continuous parameters	Compliance parameters
EN ISO 11925-2 (*) (5) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	F _s ≤ 150 mm Ignition filter paper	6	(-)	Yes	(-)	Yes
			(-)	No	(-)	No
	F _s ≤ 150 mm Ignition filter paper	6	(-)	Yes	(-)	Yes
			(-)	No	(-)	No
(*) The material didn't melt nor pull away from the pilot burner. (5) Based on the results obtained in test report No. 22082AB - CORE TYPE 1 – A.12.1.8 – SATIN – 6 mm						
EN ISO 11925-2 (*) (6) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	F _s ≤ 150 mm Ignition filter paper	6	(-)	Yes	(-)	Yes
			(-)	No	(-)	No
	F _s ≤ 150 mm Ignition filter paper	6	(-)	Yes	(-)	Yes
			(-)	No	(-)	No
(*) The material didn't melt nor pull away from the pilot burner. (6) Based on the results obtained in test report No. 22082AC - CORE TYPE 1 – M21.8.1 – SATIN – 6 mm						
EN ISO 11925-2 (*) (7) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	F _s ≤ 150 mm Ignition filter paper	6	(-)	Yes	(-)	Yes
			(-)	No	(-)	No
	F _s ≤ 150 mm Ignition filter paper	6	(-)	Yes	(-)	Yes
			(-)	No	(-)	No
(*) The material didn't melt nor pull away from the pilot burner. (7) Based on the results obtained in test report No. 22082AD - CORE TYPE 2 – NA17 – MATT ROCK – 8 mm						
EN ISO 11925-2 (*) (8) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	F _s ≤ 150 mm Ignition filter paper	6	(-)	Yes	(-)	Yes
			(-)	No	(-)	No
	F _s ≤ 150 mm Ignition filter paper	6	(-)	Yes	(-)	Yes
			(-)	No	(-)	No
(*) The material didn't melt nor pull away from the pilot burner. (8) Based on the results obtained in test report No. 22082AE - CORE TYPE 2 – A.12.1.8 – SATIN – 8 mm						

(-) Not applicable.

(**) The internal product definitions are, in comparison with the test reports and the exap report, mentioned without the resin type and core type. The resin type and core type are known by the laboratory.

Official test results used for the classification ()**

Test method	Parameter	Number of tests	Results		Criteria for Class D-s2,d0	
			Continuous parameters Mean	Compliance parameters	Continuous parameters	Compliance parameters
EN ISO 11925-2 (*) (9) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	$F_s \leq 150$ mm Ignition filter paper $F_s \leq 150$ mm Ignition filter paper	6 6	(-) (-) (-) (-)	Yes No Yes No	(-) (-) (-) (-)	Yes No Yes No
(*) The material didn't melt nor pull away from the pilot burner. (9) Based on the results obtained in test report No. 22082AF - CORE TYPE 2 – M21.8.1 – OBLIQUE – 8 mm						
EN ISO 11925-2 (*) (10) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	$F_s \leq 150$ mm Ignition filter paper $F_s \leq 150$ mm Ignition filter paper	6 6	(-) (-) (-) (-)	Yes No Yes No	(-) (-) (-) (-)	Yes No Yes No
(*) The material didn't melt nor pull away from the pilot burner. (10) Based on the results obtained in test report No. 22082AG - CORE TYPE 3 – A12.1.8 – SATIN – 6 mm						
EN ISO 11925-2 (*) (11) 30 s flame application: <u>Surface exposure</u> - front side <u>Edge exposure</u> - mid point 1,5 mm behind surface	$F_s \leq 150$ mm Ignition filter paper $F_s \leq 150$ mm Ignition filter paper	6 6	(-) (-) (-) (-)	Yes No Yes No	(-) (-) (-) (-)	Yes No Yes No
(*) The material didn't melt nor pull away from the pilot burner. (11) Based on the results obtained in test report No. 22082AH - CORE TYPE 3 – M21.8.1 – SATIN – 6 mm						
EN 13823 (12)	FIGRA _{0,2 MJ} (W/s) FIGRA _{0,4 MJ} (W/s) LFS _{<edge} THR _{600s} (MJ) SMOGRA (m²/s²) TSP _{600s} (m²) Flaming droplets/particles f < 10 s f > 10 s	3	198 198 (-) 28,4 4 43 (-) (-)	(-) (-) (-) (-) (-) (-) No No	(-) ≤ 750 (-) (-) ≤ 180 ≤ 200 (-) (-)	(-) (-) (-) (-) (-) (-) No No
(12) Based on the results obtained in test report No. 22082L - CORE TYPE 1 – NA17 – MATT ROCK – 8 mm						

(-) Not applicable.

(**) The internal product definitions are, in comparison with the test reports and the exap report, mentioned without the resin type and core type. The resin type and core type are known by the laboratory.

Official test results used for the classification (*)

Test method	Parameter	Number of tests	Results		Criteria for Class D-s2,d0	
			Continuous parameters Mean	Compliance parameters	Continuous parameters	Compliance parameters
EN 13823 (13)	FIGRA _{0,2 MJ} (W/s)	3	189	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		189	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		26,1	(-)	(-)	(-)
	SMOGRA (m²/s²)		6	(-)	≤ 180	(-)
	TSP _{600s} (m²)		53	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
(13) Based on the results obtained in test report No. 22082M - CORE TYPE 1 – A.12.1.8 – SATIN – 8 mm						
EN 13823 (14)	FIGRA _{0,2 MJ} (W/s)	3	238	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		238	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		36,0	(-)	(-)	(-)
	SMOGRA (m²/s²)		6	(-)	≤ 180	(-)
	TSP _{600s} (m²)		63	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
(14) Based on the results obtained in test report No. 22082N - CORE TYPE 1 – M21.8.1 – OBLIQUE – 8 mm						
EN 13823 (15)	FIGRA _{0,2 MJ} (W/s)	3	294	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		294	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		41,3	(-)	(-)	(-)
	SMOGRA (m²/s²)		6	(-)	≤ 180	(-)
	TSP _{600s} (m²)		41	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
(15) Based on the results obtained in test report No. 22082P - CORE TYPE 1 – NA17 – MATT ROCK – 6 mm						

(-) Not applicable.

(*) The internal product definitions are, in comparison with the test reports and the exap report, mentioned without the resin type and core type. The resin type and core type are known by the laboratory.

Official test results used for the classification (*)

Test method	Parameter	Number of tests	Results		Criteria for Class D-s2,d0	
			Continuous parameters Mean	Compliance parameters	Continuous parameters	Compliance parameters
EN 13823 (16)	FIGRA _{0,2 MJ} (W/s)	3	302	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		302	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		43,2	(-)	(-)	(-)
	SMOGRA (m²/s²)		8	(-)	≤ 180	(-)
	TSP _{600s} (m²)		58	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
	(16) Based on the results obtained in test report No. 22082Q - CORE TYPE 1 – A.12.1.8 – SATIN – 6 mm					
EN 13823 (17)	FIGRA _{0,2 MJ} (W/s)	3	303	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		303	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		43,8	(-)	(-)	(-)
	SMOGRA (m²/s²)		6	(-)	≤ 180	(-)
	TSP _{600s} (m²)		59	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
	(17) Based on the results obtained in test report No. 22082R - CORE TYPE 1 – M21.8.1 – SATIN – 6 mm					
EN 13823 (18)	FIGRA _{0,2 MJ} (W/s)	3	186	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		186	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		13,3	(-)	(-)	(-)
	SMOGRA (m²/s²)		4	(-)	≤ 180	(-)
	TSP _{600s} (m²)		50	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
	(18) Based on the results obtained in test report No. 22082S - CORE TYPE 2 – NA17 – MATT ROCK – 8 mm					

(-) Not applicable.

(*) The internal product definitions are, in comparison with the test reports and the exap report, mentioned without the resin type and core type. The resin type and core type are known by the laboratory.

Official test results used for the classification (*)

Test method	Parameter	Number of tests	Results		Criteria for Class D-s2,d0	
			Continuous parameters Mean	Compliance parameters	Continuous parameters	Compliance parameters
EN 13823 (19)	FIGRA _{0,2 MJ} (W/s)	3	139	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		131	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		14,3	(-)	(-)	(-)
	SMOGRA (m²/s²)		4	(-)	≤ 180	(-)
	TSP _{600s} (m²)		54	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
	(19) Based on the results obtained in test report No. 22082T - CORE TYPE 2 – A.12.1.8 – SATIN – 8 mm					
EN 13823 (20)	FIGRA _{0,2 MJ} (W/s)	3	138	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		138	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		13,9	(-)	(-)	(-)
	SMOGRA (m²/s²)		6	(-)	≤ 180	(-)
	TSP _{600s} (m²)		81	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
	(20) Based on the results obtained in test report No. 22082U - CORE TYPE 2 – M21.8.1 – OBLIQUE – 8 mm					
EN 13823 (21)	FIGRA _{0,2 MJ} (W/s)	3	151	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		151	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		18,7	(-)	(-)	(-)
	SMOGRA (m²/s²)		7	(-)	≤ 180	(-)
	TSP _{600s} (m²)		71	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
	(21) Based on the results obtained in test report No. 22082V - CORE TYPE 3 – A12.1.8 – SATIN – 6 mm					

(-) Not applicable.

(*) The internal product definitions are, in comparison with the test reports and the exap report, mentioned without the resin type and core type. The resin type and core type are known by the laboratory.

Official test results used for the classification (*)

Test method	Parameter	Number of tests	Results		Criteria for Class D-s2,d0	
			Continuous parameters Mean	Compliance parameters	Continuous parameters	Compliance parameters
EN 13823 (22)	FIGRA _{0,2 MJ} (W/s)	5	138	(-)	(-)	(-)
	FIGRA _{0,4 MJ} (W/s)		138	(-)	≤ 750	(-)
	LFS _{<edge}		(-)	(-)	(-)	(-)
	THR _{600s} (MJ)		18,5	(-)	(-)	(-)
	SMOGRA (m²/s²)		5	(-)	≤ 180	(-)
	TSP _{600s} (m²)		61	(-)	≤ 200	(-)
	Flaming droplets/particles					
	f < 10 s		(-)	No	(-)	No
	f > 10 s		(-)	No	(-)	No
(22) Based on the results obtained in test report No. 22082W - CORE TYPE 3 – M21.8.1 – SATIN – 6 mm						

(-) Not applicable.

(*) The internal product definitions are, in comparison with the test reports and the exap report, mentioned without the resin type and core type. The resin type and core type are known by the laboratory.

3. CLASSIFICATION AND FIELD OF APPLICATION

a) Reference of classification

This classification has been carried out in accordance with EN 13501-1:2018.

The related harmonized product standard is EN 438-7:2005 and has been used for the direct field of application and for the mounting and fixing of the SBI-test specimens.

b) Classification

The product **Trespa® Toplab® Vertical** in relation to its reaction to fire behavior is classified as:

Fire behavior	Smoke production	Flaming droplets
D	s2	d0

c) Field of application

This classification for the product as described in §1b, is valid for the following end use applications:

- Substrate: Wood based substrates of Euro class D-s2,d0 or better and any other substrate of Euro class A1 and A2-s1,d0, with a thickness of at least 10 mm and a density of at least 510 kg/m³
- With an open air gap
- Fixing: Mechanically fixed on all types of supporting frames (wood, aluminium, steel frames) with fixing distances of up to 800 mm
- With or without an open horizontal joint (maximum 8 mm) between the HPL panels, and with any type of closed horizontal joint
- With or without an open (maximum 8 mm) vertical joint between the HPL panels
- With or without insulation as tested (in accordance with § B.2 of EN 438-7:2005)
- Fire exposed side: decor layer

This classification is valid for the following product parameters:

STD grade HPL-panels with core type 1 (*)	STD grade HPL-panels with core type 2 (*)	STD grade HPL panels with core type 3 (*)
Nominal density: 1350 kg/m ³		
Without fire retardants		
Valid for single sided and double sided panels		
Valid for the following surface textures: satin, matt-rock, diffuse, oblique, specular and matt (see Figure 1)		
Valid for thicknesses 6 mm and all greater thicknesses		Valid for thicknesses 8 mm and all greater thicknesses
Valid for all colours within the UNI colourgroup (A,L)	Valid for all colours within the UNI colourgroup (A,L)	Valid for all colours within the UNI colourgroup (A,L)
Valid for all colours within the Metallics colourgroup (M,LM)	Valid for all colours within the Metallics colourgroup (M,LM)	Valid for all colours within the Metallics colourgroup (M,LM)
Valid for all colours within the printend decor colourgroup (NA,NM,NW,C,CM)		Valid for all colours within the printend decor colourgroup (NA,NM,NW,C,CM)

(*) Type of resin and core type are known by the laboratory

4. RESTRICTIONS

At the time the standard EN 13501-1:2018 was published, no decision was made concerning the duration of validity of a classification report.

Provisions of Regulation (EU) 305/2011, commonly known as the Construction Products Regulation (CPR), prevail over any conflicting provisions in the harmonized standards and technical specifications.

5. WARNING

This classification report does not represent type approval or certification of the product.

This classification report does not represent type approval or certification of the product. The classification assigned to the product in this report is appropriate to a Declaration of Performance (DoP) by the manufacturer within the context of System 1 of AVCP and CE marking under the Regulation 305/2011/EU of the European Parliament and of the Council of 9 March 2011 laying down harmonized conditions for the marketing of construction products.

The test laboratory has played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide evidence for the traceability of the samples tested.

PREPARED BY

	Ruben Vercouter (Signature) Project Coordinator, under supervision of Niek de Pauw Ghent 2023.06.08 09:16:49 +02'00'
---	--

APPROVED BY

	Niek De Pauw (Signature) Senior Project Lead Ghent 2023.06.12 12:02:00 +02'00'
--	---

This document is the original version of this classification report and is written in English.
This report may be used only literally and completely for publications. - For publications of certain texts, in which this report is mentioned, our permission must be obtained in advance.
The authenticity of the electronic signatures is assured by Belgium Root CA.